

REPORT D

AD-A253 729

1a REPORT SECURITY CLASSIFICATION

Unclassified

2a SECURITY CLASSIFICATION AUTHORITY

2b DECLASSIFICATION / DOWNGRADING SCHEDULE

AUG 6 1992

Unlimited

4 PERFORMING ORGANIZATION REPORT NUMBER(S)

14

5 MONITORING ORGANIZATION REPORT NUMBER(S)

6a NAME OF PERFORMING ORGANIZATION

NIST

6b OFFICE SYMBOL  
(if applicable)

7a NAME OF MONITORING ORGANIZATION

ONR

6c ADDRESS (City, State, and ZIP Code)

A329, Materials Building  
Gaithersburg, Md 20899

7b ADDRESS (City, State, and ZIP Code)

Code 1131  
800 N. Quincy Street  
Arlington, VA 22217-50008a NAME OF FUNDING / SPONSORING  
ORGANIZATION

ONR

8b OFFICE SYMBOL  
(if applicable)

9. PROCUREMENT INSTRUMENT IDENTIFICATION NUMBER

N00014-90-F-0011

8c ADDRESS (City, State, and ZIP Code)

10 SOURCE OF FUNDING NUMBERS

PROGRAM  
ELEMENT NOPROJECT  
NOTASK  
NOWORK UNIT  
NO

11 TITLE (Include Security Classification)

Moire-Fringe Images of Twin Boundaries in Chemical Vapor Deposited Diamond

12 PERSONAL AUTHOR(S)

D. Shechtman, A. Feldman, M.D. Vaudin, and J.L. Hutchison

13a. TYPE OF REPORT

Interim

13b. TIME COVERED

FROM TO

14 DATE OF REPORT (Year, Month, Day)

92-07-10

15. PAGE COUNT

13

16 SUPPLEMENTARY NOTATION

17 COSATI CODES

FIELD

GROUP

SUB-GROUP

18. SUBJECT TERMS (Continue on reverse if necessary and identify by block number)

This document has been approved for public release and  
sale: its distribution is unlimited

19 ABSTRACT (Continue on reverse if necessary and identify by block number)

Features in lattice image micrographs of chemical vapor deposited diamond can be interpreted as Moire fringes that occur when viewing twin boundaries that are inclined to the electron beam. The periodicities in images of inclined twin boundaries with  $\Sigma=3$  and  $\Sigma=9$  misorientations have been modeled by computer graphic simulation.

20 DISTRIBUTION / AVAILABILITY OF ABSTRACT

☒ UNCLASSIFIED/UNLIMITED ☐ SAME AS RPT ☐ DTIC USERS

21. ABSTRACT SECURITY CLASSIFICATION

Unclassified

22a NAME OF RESPONSIBLE INDIVIDUAL

22b TELEPHONE (Include Area Code)

22c OFFICE SYMBOL

DTIC QUALITY INSPECTED 5

OFFICE OF NAVAL RESEARCH

Contract N00014-90-F-0011

R&T Project No. IRMT 025

TECHNICAL REPORT No. 14

MOIRE-FRINGE IMAGES OF TWIN BOUNDARIES IN  
CHEMICAL VAPOR DEPOSITED DIAMOND

D. Shechtman\*, A. Feldman, M.D. Vaudin, and J.L. Hutchison\*\*

submitted to

Applied Physics Letters

National Institute of Standards and Technology

Ceramics Division

Gaithersburg, MD 20899

July 10, 1992

Reproduction in whole or in part is permitted for  
any purpose of the United States Government

This document has been approved for public release  
and sale; its distribution is unlimited

\*Visiting scientist at the Johns Hopkins University and at NIST from the Technion, Israel.

\*\* University of Oxford, England

Accession For	
NTIS GRA&I	<input checked="checked" type="checkbox"/>
DTIC TAB	<input type="checkbox"/>
Unannounced	<input type="checkbox"/>
Justification	
By	
Distribution/	
Availability Codes	
Dist	Avail and/or Special
A-1	

02 8 04 004

92-20917



# **MOIRE-FRINGE IMAGES OF TWIN BOUNDARIES IN CHEMICAL VAPOR DEPOSITED DIAMOND<sup>a)</sup>**

**Dan Shechtman<sup>b)</sup>**

**Department of Materials Engineering  
Technion, Haifa, 32000, Israel**

**Albert Feldman and Mark D. Vaudin**

**Ceramics Division**

**Materials Science and Engineering Laboratory**

**National Institute of Standards and Technology<sup>c)</sup>  
Gaithersburg MD 20899**

**and**

**John L. Hutchison**

**Department of Materials**

**University of Oxford**

**Oxford OX1 3PH, England**

## **ABSTRACT**

Features in lattice image micrographs of chemical vapor deposited diamond can be interpreted as Moire fringes that occur when viewing twin boundaries that are inclined to the electron beam. The periodicities in images of inclined twin boundaries with  $\Sigma=3$  and  $\Sigma=9$  misorientations have been modeled by computer graphic simulation.

**Key words:** chemical vapor deposition, CVD, diamond, twins, lattice images, Moire fringes

---

<sup>a)</sup>This work was supported in part by the U.S. Office of Naval Research.

<sup>b)</sup>Visiting Professor at the Johns Hopkins University and Guest Scientist at the National Institute of Standards and Technology.

<sup>c)</sup>Technology Administration, U.S. Department of Commerce

## MOIRE-FRINGE IMAGES OF TWIN BOUNDARIES IN CHEMICAL VAPOR DEPOSITED DIAMOND

Recent work strongly suggests that lattice defects such as twins and stacking faults play an important role in the growth of diamond films prepared by chemical vapor deposition (CVD)<sup>1</sup>. CVD diamond usually grows as a polycrystalline material consisting of highly twinned grains. Typically, each grain is not a single crystal but consists of many twins, each twin within the grain having a well defined orientation with respect to every other twin within the grain. All of the twins observed in CVD diamond have a common  $\langle 110 \rangle$  rotation axis.

High resolution transmission electron microscopy (HRTEM) of CVD diamond has revealed a variety of twin boundary types<sup>1-8</sup>. Narayan<sup>3</sup> has noted the presence of twin boundaries classified as  $\Sigma=3$  (first order twins) and  $\Sigma=9$  (second order twins) in the nomenclature of the coincident site lattice (CSL)<sup>9</sup>, where the order  $n$  of the twin boundary is such that  $\Sigma=3^n$ . Twin boundaries have been observed previously in other cubic materials having the diamond lattice structure, such as silicon<sup>10-12</sup> and germanium<sup>13</sup>. In addition to the twin boundaries observed by Narayan, boundaries of types  $\Sigma=27$  and  $\Sigma=81$  have also been observed in CVD diamond<sup>14</sup> and examples are shown in this letter.

In this letter, we report on several Moire-fringe features observed in high resolution lattice images of CVD diamond. We interpret these features as images of twin boundaries of types  $\Sigma=3$  and  $\Sigma=9$  where the boundary surface is inclined to the electron beam; the beam passes through both of the twin-related crystals and double diffraction occurs. The periodicities in the resultant image depend on the relative orientations of the twins. By overlapping computer-generated  $\langle 110 \rangle$  projections of the diamond lattice at the misorientation angles of the crystals, the principal features seen in these lattice images are reproduced.

We have examined the twinning structure of a fine-grained diamond film grown by microwave-assisted chemical vapor deposition on a single crystal silicon substrate. The film growth parameters were: microwave power - 1 kW; nominal graphite susceptor temperature - 650 °C; gas pressure -  $6.6 \times 10^3$  Pa; gas flow rate - 260 standard cm<sup>3</sup>/min; gas composition - 99.5% H<sub>2</sub>, 0.5% CH<sub>4</sub>; deposition time - 45 min; growth rate - 0.4  $\mu\text{m}/\text{h}$ ; total thickness - 0.3  $\mu\text{m}$ ; average grain size -  $\sim 0.1 \mu\text{m}$ . The details of the specimen preparation and the HRTEM technique are given in Ref.[1].

We classify the twin boundaries into two categories. The first category consists of planar tilt boundaries lying on crystallographic planes that mirror the bordering twins; these are called 'coherent' boundaries. The second category consists of boundaries that rarely lie on well-defined crystallographic planes and whose orientations may vary from place to place. In this paper, we call these 'noncoherent' boundaries.

Figure 1 shows both coherent and noncoherent twin boundaries in the CVD diamond

specimen. The coherent boundaries are all of type  $\Sigma=3$ . A noncoherent boundary can be observed meandering across the micrograph. Where the boundary is parallel to the electron beam (V), its image is lighter than the images of coherent boundaries because of preferential ion thinning; this suggests that the noncoherent boundary has greater energy than the coherent boundaries. From the relative orientations of the  $\{111\}$  planes on opposite sides of a boundary, we have identified noncoherent boundaries of types  $\Sigma=3$  and  $\Sigma=9$ . Noncoherent twin boundaries of types  $\Sigma=27$  and  $\Sigma=81$  can be seen in Fig. 2, which shows a region containing a twin quintuplet (discussed below).

In CVD diamond,  $\Sigma=9$ ,  $\Sigma=27$  and  $\Sigma=81$  boundaries are usually observed to be noncoherent. This is in marked contrast to observations made in silicon, where  $\Sigma=9$  and  $\Sigma=27$  boundaries are usually coherent<sup>10,15,16</sup>. Noncoherent boundaries arise when the free surfaces of two twin-related crystals grow toward each other and meet at an arbitrary surface. Because of the relatively low homologous temperature of CVD diamond during the deposition process (650 °C), the atoms in the boundary region have insufficient energy to rearrange once the twins have met; therefore, the boundary plane cannot rotate into a more symmetrical and lower energy orientation. The boundary that is formed results from the detailed kinetics and energetics of the diamond growth specific to a particular specimen. Thus, a noncoherent boundary can even occur when two crystals of the same orientation grow together. There may be some slight displacement of the two crystals relative to each other and there is insufficient energy to allow the boundary to annihilate. Such a displacement is seen in Fig. 1 (W), where two crystals of identical orientation have formed an interface of relatively low density.

Noncoherent boundaries can arise during the early stages of the nucleation and growth of a diamond twin quintuplet, a structure frequently observed to be the origin of growth of a grain<sup>3,7,14</sup>. An example is shown in Fig. 2 where the center of the twin quintuplet is marked  $\star$ . Figure 3(a) shows a computer simulation of the twin quintuplet in  $\langle 110 \rangle$  projection; in three dimensions, the twin quintuplet consists of five successive tilt boundaries radiating from a common  $\langle 110 \rangle$  rotation axis. Four of the boundaries are coherent twin boundaries of type  $\Sigma=3$  with a tilt angle of 70.53°. The fifth boundary is of type  $\Sigma=81$  with a tilt angle of 77.88°. The difference between the  $\Sigma=81$  tilt and the  $\Sigma=3$  tilt leaves a small mismatch angle of 7.35° between  $\{111\}$  planes in the twins separated by the  $\Sigma=81$  boundary as shown in Fig. 3. The  $\Sigma=81$  boundary can be modeled as a  $\Sigma=3$  twin boundary containing regularly spaced secondary dislocations to accommodate the mismatch angle<sup>10</sup>. However because of the low homologous temperature referred to above and because this boundary is the last to form during nucleation of a twin quintuplet, the boundary forms in a noncoherent manner inherent to the quintuplet structure.

Several regions in Fig. 1 do not exhibit the typical appearance of  $\langle 110 \rangle$  oriented diamond evident throughout most the micrograph. In all cases, these anomalous regions are associated with the noncoherent boundary. The images in these regions can be interpreted as Moire-fringe patterns that result when the twin boundaries are inclined with respect to the electron beam so that the beam passes through two overlapping twins. In Fig. 1, overlapping

twins with boundaries of type  $\Sigma=3$  are indicated by X and with boundaries of type  $\Sigma=9$  are indicated by Y.

We have modeled the periodicities observed in the images of the inclined  $\Sigma=3$  and  $\Sigma=9$  noncoherent boundaries using a graphical projection of the diamond lattice viewed along the  $\langle 110 \rangle$  direction. In the twin quintuplet modeled in Fig. 3(a), each twin is bounded by  $\{111\}$  planes; no attempt has been made to model the  $\Sigma=81$  boundary. We have divided the figure into 5 twin domains labeled A, B, C, D and E. Table 1 identifies the boundary type that would occur if one twin, oriented as defined in the twin quintuplet figure, were to border another. If we enlarge the twin in region A to overlap the entire twin quintuplet, we obtain overlap patterns with the periodicities of the CSLs having  $\Sigma=3$ ,  $\Sigma=9$ ,  $\Sigma=27$  and  $\Sigma=81$  misorientations (Fig. 3(b)). The overlap of region A with region B shows a striped pattern having the same periodicity as the  $\Sigma=3$  overlap region labeled X in Fig. 1. The overlap of region A with region C shows a centered hexagonal pattern having the same periodicities as the  $\Sigma=9$  overlap region labeled Y in Fig. 1. Furthermore, the relative orientations of the  $\Sigma=3$  CSL, the  $\Sigma=9$  CSL, and the non-overlapping regions seen in Fig. 3(b) are the same as the relative orientations of the stripes in region X, the hexagonal patterns in region Y and the non-overlapping crystals seen in Fig. 1.

In conclusion, high resolution lattice images of CVD diamond have revealed a highly varied twinning structure. Moire-fringe patterns observed in the micrographs can be interpreted as overlapping twins with boundaries of types  $\Sigma=3$  and  $\Sigma=9$  that are inclined to the electron beam. A computer graphic simulation has been made to duplicate the periodicities and orientations of these boundary images. The patterns we have identified as being due to overlapping twins show the same periodicities and orientations as the corresponding coincidence site lattices.


## REFERENCES

1. D. Shechtman, E.N. Farabaugh, L.H. Robins, A. Feldman and J.L. Hutchison, in *Diamond Optics IV*, A. Feldman and S. Holly, Editors, SPIE Proc. 1534, 26-43 (1991).
2. B.E. Williams and J.T. Glass, *J. Mater. Res.* 4, 373 (1989).
3. J. Narayan, *J. Mater. Res.* 5, 2414 (1990).
4. B.E. Williams, J.T. Glass, R.F. Davis, K. Kobashi and K.L. More, *Proc. 1st Int. Symp. Diamond and Diamond Like Films*, J.P. Dismukes, editor 202 (1989).
5. G-H.M. Ma, Y.H. Lee and J.T. Glass, *J. Mater. Res.* 5, 2367 (1990).
6. J. Narayan, A.R. Srivatsa, M. Peters S. Yokota and K.V. Ravi, *Appl. Phys. Lett.* 53, 1823 (1988).


7. B.E. Williams, H.S. Kong and J.T. Glass, J. Mater. Res. 5, 801 (1990).
8. K. Kobashi, K. Nishimura, K. Miyata, Y. Kawate, J.T. Glass and B.E. Williams, SPIE Diamond Optics, 969, 159 (1988).
9. W. Bollman, Crystal Defects and Crystalline Interfaces (Springer-Verlag, New York, 1970).
10. M.D Vaudin, B. Cunningham and D.G. Ast, Scripta Met. 17, 191 (1983).
11. S. Iijima, Jpn. J. Appl. Phys. 26, 357 (1987).
12. S. Iijima, Jpn. J. Appl. Phys. 26, 365 (1987).
13. Z. Elgat, "Structure of Twin Boundaries in Ge and Spinel", Doctoral Thesis, Cornell University, August 1985.
14. D. Shechtman, E.N. Farabaugh, L.H. Robins, A. Feldman and J.L. Hutchison, in preparation.
15. B. Cunningham, H.P. Strunk and D.G. Ast, Scripta Met. 16, 349 (1982).
16. B. Cunningham, H.P. Strunk and D.G. Ast, Appl. Phys. Lett. 40(3), (1982).

Table I. Type of twin boundary occurring if one twin in Fig. 3(a), were to border another.


Boundary Type (coincidence site lattice notation)	Adjacent Regions
$\Sigma=3$	A-B, B-C, C-D, D-E
$\Sigma=9$	A-C, B-D, C-E
$\Sigma=27$	A-D, B-E
$\Sigma=81$	A-E




1. Lattice image of a CVD diamond specimen observed in a  $\langle 110 \rangle$  direction. The figure shows coherent twin boundaries of type  $\Sigma=3$ , noncoherent boundaries of types  $\Sigma=3$  and  $\Sigma=9$ , and Moiré fringes. See text for a discussion of the labeled features.



2. Lattice image of CVD diamond containing a twin quintuplet observed in a  $\langle 110 \rangle$  direction.  $\Sigma=3$ ,  $\Sigma=9$ ,  $\Sigma=27$ , and  $\Sigma=81$  boundaries can be observed.



(a)



(b)

3. (a) Computer model of a twin quintuplet where the  $\{111\}$  planes bounding in each of the twins are indicated by the lines. (b) Overlapping twins having coincidence site lattices of types  $\Sigma=3$ ,  $\Sigma=9$ ,  $\Sigma=27$  and  $\Sigma=81$ . The simulations are observed along a  $\langle 110 \rangle$  direction.

## Distribution List

Mr. James Arendt  
Hughes Aircraft Company  
8433 Fallbrook Avenue 270/072  
Canoga Park, CA 91304  
(838) 702-2890

Mr. Larry Blow  
General Dynamics  
1525 Wilson Blvd., Suite 1200  
Arlington, VA 22209  
(703) 284-9107

Mr. Ellis Boudreaux  
Code AGA  
Air Force Armament Laboratory  
Eglin AFB, FL 32542

Dr. Duncan W. Brown  
Advanced Technology Materials, Inc.  
7 Commerce Drive  
Danbury, CT 06810-4131

Dr. Mark A. Cappelli  
Stanford University  
Mechanical Engineering Department  
Stanford, CA 94305  
(415) 723-1745

Dr. R. P. H. Chang  
Materials Science & Engineering Dept.  
2145 Sheridan Road  
Evanston, IL 60208  
(312) 491-3598

Defense Documentation Center  
Cameron Station  
Alexandria, VA 22314  
(12 copies)

Dr. Bruce Dunn  
UCLA  
Chemistry Department  
Los Angeles, CA 90024  
(213) 825-1519

Dr. Al Feldman  
Leader, Optical Materials Group  
Ceramics Division  
Materials Science & Engineering Lab  
NIST  
Gaithersburg, MD 20899  
(301) 975-5740

Dr. John Field  
Department of Physics  
University of Cambridge  
Cavendish Laboratory  
Madingley Road  
Cambridge CB3 0HE  
England  
44-223-3377333 Ext. 7318

Dr. William A. Goddard, III  
Director, Materials and Molecular  
Simulation Center  
Beckman Institute  
California Institute of Technology  
Pasadena, CA 91125  
(818) 356-6544 Phone  
(818) 568-8824 FAX

Dr. David Goodwin  
California Institute of Technology  
Mechanical Engineering Dept.  
Pasadena, CA 91125  
(818) 356-4249

Dr. Kevin Gray  
Norton Company  
Goddard Road  
Northboro, MA 01532  
(508) 393-5968

**Mr. Gordon Griffith**  
**WRDC/MLPL**  
**Wright-Patterson AFB, OH 45433**

**Dr. H. Guard**  
**Office of Chief of Naval Research**  
**(ONR Code 1113PO)**  
**800 North Quincy Street**  
**Arlington, VA 22217-5000**

**Dr. Alan Harker**  
**Rockwell Int'l Science Center**  
**1049 Camino Dos Rios**  
**P.O. Box 1085**  
**Thousand Oaks, CA 91360**  
**(805) 373-4131**

**Mr. Stephen J. Harris**  
**General Motors Research Laboratories**  
**Physical Chemistry Department**  
**30500 Mound Road**  
**Warren, MI 48090-9055**  
**(313) 986-1305 Phone**  
**(313) 986-8697 FAX**  
**E-mail: SHARRIS@GMR.COM**

**Mr. Rudolph A. Heinecke**  
**Standard Telecommunication**  
**Laboratories, Ltd.**  
**London Road**  
**Harlow, Essex CM17 9MA**  
**England**  
**44-279-29531 Ext. 2284**

**Dr. Kelvin Higa**  
**Code 3854**  
**Naval Weapons Center**  
**China Lake, CA 93555-6001**

**Dr. Curt E. Johnson**  
**Code 3854**  
**Naval Weapons Center**  
**China Lake, CA 93555-6001**  
**(619) 939-1631**

**Dr. Larry Kabacoff (Code R32)**  
**Officer in Charge**  
**Naval Surface Weapons Center**  
**White Oak Laboratory**  
**10901 New Hampshire**  
**Silver Spring, MD 20903-5000**

**Mr. M. Kinna**  
**Office of Chief of Naval Research**  
**(ONT Code 225)**  
**800 North Quincy Street**  
**Arlington, VA 22217-5000**

**Dr. Paul Klocek**  
**Texas Instruments**  
**Manager, Advanced Optical Materials Br.**  
**13531 North Central Expressway**  
**P.O. Box 655012, MS 72**  
**Dallas, TX 75268**  
**(214) 995-6865**

**Ms. Carol R. Lewis**  
**Jet Propulsion Laboratory**  
**4800 Oak Grove Drive**  
**Mail Stop 303-308**  
**Pasadena, CA 91109**  
**(818) 354-3767**

**Dr. J.J. Mecholsky, Jr.**  
**University of Florida**  
**Materials Science & Engineering Dept.**  
**256 Rhines Hall**  
**Gainesville, FL 32611**  
**(904) 392-1454**

**Dr. Russell Messier**  
**202 Materials Research Laboratory**  
**Pennsylvania State University**  
**University Park, PA 16802**  
**(814) 865-2326**

**Mr. Mark Moran**  
**Code 3817**  
**Naval Weapons Center**  
**China Lake, CA 93555-6001**

**Mr. Ignacio Perez**  
Code 6063  
Naval Air Development Center  
Warminster, PA 18974  
(215) 441-1681

**Mr. C. Dale Perry**  
U.S. Army Missile Command  
AMSMI-RD-ST-CM  
Redstone Arsenal, AL 35898-5247

**Mr. Bill Phillips**  
Crystallume  
125 Constitution Drive  
Menlo Park, CA 94025  
(415) 324-9681

**Dr. Rishi Raj**  
Cornell University  
Materials Science & Engineering Dept.  
Ithaca, NY 14853  
(607) 255-4040

**Dr. M. Ross**  
Office of Chief of Naval Research  
(ONR Code 1113)  
800 North Quincy Street  
Arlington, VA 22217-5000

**Dr. Rustum Roy**  
102A Materials Research Laboratory  
Pennsylvania State University  
University Park, PA 16802  
(814) 863-7040 FAX

**Dr. James A. Savage**  
Royal Signals & Radar Establishment  
St. Andrews Road  
Great Malvern, Worcs WR14.3PS  
England  
01-44-684-895043

**Mr. David Siegel**  
Office of Chief of Naval Research  
(ONT Code 213)  
800 North Quincy Street  
Arlington, VA 22217-5000

**Dr. Keith Snail**  
Code 6520  
Naval Research Laboratory  
Washington, DC 20375  
(202) 767-0390

**Dr. Y. T. Tzeng**  
Auburn University  
Electrical Engineering Department  
Auburn, AL 36849  
(205) 884-1869

**Dr. Terrell A. Vanderah**  
Code 3854  
Naval Weapons Center  
China Lake, CA 93555-6001  
(619) 939-1654

**Dr. George Walrafen**  
Howard University  
Chemistry Department  
525 College Street NW  
Washington, DC 20059  
(202) 806-6897/6564

**Mr. Roger W. Whatmore**  
Plessey Research Caswell Ltd.  
Towcester Northampton NN128EQ  
England  
(0327) 54760

**Dr. Charles Willingham**  
Raytheon Company  
Research Division  
131 Spring Street  
Lexington, MA 02173  
(617) 830-3061

Dr. Robert E. Witkowski  
Westinghouse Electric Corporation  
1310 Beulah Road  
Pittsburgh, PA 15235  
(412) 256-1173

Dr. Aaron Wold  
Brown University  
Chemistry Department  
Providence, RI 02912  
(401) 863-2857

Dr. Walter A. Yarbrough  
260 Materials Research Laboratory  
Pennsylvania State University  
University Park, PA 16802  
(814) 865-2326

Mr. M. Yoder  
Office of Chief of Naval Research  
(ONR Code 1114SS)  
800 North Quincy Street  
Arlington, VA 22217-5000

Dr. Robert Pohanka (Code 1131)  
Office Of Naval Research  
800 N. Quincy Street  
Arlington, VA 22217

Dr. David Nelson (Code 1113)  
Office Of Naval Research  
800 N. Quincy Street  
Arlington, VA 22217

Dr. Robert W. Schwartz (Code 38505)  
Naval Weapons Center  
China Lake, CA 93555